

# SEALANT



## FTR-SLS

### Product Data

FTR-SLS (self-leveling sealant) is an approved pitch pan sealant.

#### DESCRIPTION

FTR-SLS is a moisture curing, pourable, polyether sealant to fill pitch pans. The sealant is suitable for application in all climates. FTR-SLS is solvent free, contains no isocyanates and will not shrink upon curing. FTR-SLS has resilient elastomeric properties and excellent adhesion to most construction materials. FTR-SLS's low durometer accommodates greater movement in penetration seals than typical urethane sealants.

Refer to FiberTite Specifications and Details for proper pitch pan installation.

#### STORAGE

Store original, unopened containers in a cool, dry area. Protect unopened containers from water, heat and direct sunlight. Elevated temperatures will reduce FTR-SLS's shelf life.

##### Shelf Life:

One year from date of manufacturer when stored in normal environments. High temperature and high relative humidity may significantly reduce shelf life.

#### CURE TIME

FTR-SLS is a moisture cure sealant. Rate of cure is dependent on atmospheric conditions. Curing proceeds at a rate of 1/4" a week at 70°F and 50% Relative Humidity. Lower temperature and humidity will inhibit the rate of cure. Higher temperature and humidity will accelerate rate of cure. Depths greater than 2" will cure through in 2 to 3 months.

#### CLEAN UP

Wet adhesive can be removed using a solvent such as alcohol. Cured FTR-SLS can be removed by abrading or scraping the substrate.

#### GREEN STANDARDS:

- LEED 2.2 for New Construction and Major Renovations: Low Emitting Materials (Section 4.1) 1 Point
- NAHB Model Green Home Building Guidelines: 5 Global Impact Points
- VOC Content: less than 19 grams / liter ASTM D2369 EPA Method 24 (tested at 240°F / 115°C)

These specifications are current as of the date of printing. Revisions or additions may be issued periodically. For a listing, presentation, and download of the most recent data, visit:

[www.FiberTite.com/document-library/product-data-sheets](http://www.FiberTite.com/document-library/product-data-sheets)

#### PHYSICAL PROPERTIES

Container	28-oz cartridge
Cartridges per Carton	12
Color	Gray

#### ADVANTAGES

- Solvent free, 100% solids will not shrink
- 20 minute skin over
- No outgassing on damp surfaces
- Good UV stability, will not suntan
- Paintable within 24 hours (See limitations)
- Self leveling, no special tools or mixing required
- Application at temperatures as low as 32°F (0°C)

#### LIMITATIONS:

Wet adhesive can be removed using a solvent such as alcohol. Cured FTR-SLS can be removed by abrading or scraping the substrate.

#### PRECAUTIONARY DATA

- Do not store in elevated temperatures
- Do not apply at temperatures below 30°F
- Do not use petroleum-based solvents such as mineral spirits or xylene for cleaning purposes
- Maintain FTR-SLS at room temperature before applying to ensure easy gunning and leveling



For more information on FiberTite Systems and accessories please call:  
Seaman Corporation (800) 927-8578  
International (330) 262-1111  
[www.fibertite.com](http://www.fibertite.com)

**INTELLIGENT**  
ROOFING SOLUTIONS

FiberTite® is a registered trademark of Seaman Corporation.

